

## ERRATUM

### Erratum: "Crystallization kinetics of BaO–Al<sub>2</sub>O<sub>3</sub>–SiO<sub>2</sub> glasses"

[*J. Mater. Res.* **4**, 1257 (1989)]

Narottam P. Bansal and Mark J. Hyatt

*National Aeronautics and Space Administration, Lewis Research Center, Cleveland, Ohio 44135*

(Received 23 May 1990; accepted 23 May 1990)

Due to an error in compiling the data, the crystallization peak temperature ( $T_p$ ) values for glass B listed in Table III of this article are incorrect. The correct values are shown below.

TABLE III. DTA glass transition and crystallization peak temperatures at various scan rates for the barium aluminosilicate glasses.

Glass composition	Scan rate, $\theta$ °C/min	$T_p$ , °C	$T_g$ , °C <sup>a</sup>
A (powder)	2.5	994	...
	5	1008	...
	10	1023	...
	20	1039	887
	30	1053	893
	40	1062	898
B (powder)	2.5	1008	...
	5	1030	...
	10	1042	...
	20	1065	...
	30	1073	878
	40	1078	888
B (bulk)	2.5	1090	...
	5	1106	...
	10	1126	882
	20	1146	885
	30	1161	888
	40	1165	892

<sup>a</sup>From DTA.

The authors wish to thank Dr. C. S. Ray of the University of Missouri at Rolla for bringing this matter to their attention.