

Synthesis and Transformation of Carbonaceous Nanoparticles

Vito Mennella

INAF - Osservatorio Astronomico di Capodimonte, via Moiariello, 16 80131 Napoli, Italy
email: mennella@na.astro.it

Abstract. The physical properties of carbonaceous nanoparticles depend on the production conditions. In addition, these properties are modified by heat, UV and ion irradiation and gas interaction. We will discuss the synthesis and transformation of carbon nanoparticles that have been proposed as carriers of aromatic and aliphatic spectroscopic features observed in the interstellar medium.

1. Carbon particles in space

The presence in the diffuse interstellar medium of aromatic and aliphatic carbon components is inferred from the UV interstellar extinction bump and the $3.4\ \mu\text{m}$ absorption band, respectively. Interstellar and circumstellar objects in our Galaxy and many extragalactic objects emit a spectrum characterized by features generally attributed to aromatic carbon molecules such as polycyclic aromatic hydrocarbon molecules (PAHs). Fullerene have recently been confirmed in many sources of different nature. The variety of carbon species present in space is due to the nature of the carbon atom. It can have three bonding configurations sp^3 , sp^2 and sp that give rise to allotropic forms (diamond, graphite, fullerene and carbene or carbonoid material) with different optical and physical properties. Besides these forms there is great variety of disordered materials that are characterized by mixtures of carbon bonding configurations. Their properties depend on the prevailing bonding configuration. In carbon materials the atomic organization is closely related to the electronic structure and, consequently, to the optical properties.

2. Carbon particles in the laboratory

To get insight into the nature of the interstellar carbon components, analogue materials have been studied. Different methods, such as arc discharge, laser ablation, chemical vapor deposition, flame synthesis and energetic processing of carbon containing molecules at low temperature, have been applied for the production of carbon nanoparticles. The produced samples have been studied with different analytic techniques to obtain information on structure and optical properties. Laboratory simulation of grain processing in space is very important to interpret the changes of grains in different interstellar environments through an evolutionary physical-chemical scheme of materials. In fact, dust grain composition evolves through exposure to UV photons, heat, gas and cosmic rays.

On the basis of the experimental results of UV irradiation of hydrogenated carbon grains a model for the UV interstellar extinction bump was proposed (Mennella *et al.* 1998). The model relies on the extrapolation of the laboratory trend of the dielectric function as function of the UV dose to represent the UV processing pathway for hydrogenated carbon grains in the diffuse medium. Recent experimental work confirms that the UV extinction bump is consistent with UV irradiated hydrogenated carbon grains (Gadallah *et al.* 2011).

Energetic processing by UV photons and ions of aliphatic materials destroys their C-H bonds. UV irradiation of hydrogenated carbon grains and hydrocarbon molecules under simulated dense and diffuse medium conditions is indeed characterized by a strong decrease of the $3.4\ \mu\text{m}$ band (Mennella *et al.* 2001, Muñoz Caro *et al.* 2001, Gadallah *et al.* 2012). On the basis of the experimental results one can conclude that the interstellar radiation field should destroy the C-H bonds aliphatic component of diffuse regions in a very short time scale (10^4 years). A similar destruction of the aliphatic C-H bonds is observed during ion irradiation of hydrogenated carbon grains under simulated dense and diffuse interstellar medium conditions (Mennella *et al.* 2003, Godard *et al.* 2011).

Simulation of carbon dust processing under diffuse and dense medium conditions indicates that the key process for the evolution of the interstellar aliphatic carbon component is its interaction with H atoms. This interaction is able to counteract the destruction of C-H bonds by UV photons and cosmic rays and it activates the $3.4\ \mu\text{m}$ band in diffuse interstellar regions and the $3.47\ \mu\text{m}$ feature in dense clouds (Mennella *et al.* 2002, Mennella 2008). The interesting aspect is that the same carbon grain population can absorb at the two wavelengths as a consequence of evolutionary transformations caused by processing. The transformations are compatible with the time-scale required by fast cycling of materials between dense and diffuse regions of the interstellar medium.

Moreover, this carbon component, after the inclusion in a comet during the formation process in the cold outer edge of the solar nebula, may evolve to develop the CH_2 and CH_3 groups (as suggested by laboratory simulations) and contribute to the aliphatic band at $3.4\ \mu\text{m}$ of Interplanetary Dust Particles and particles of comet Wild 2 collected by the Stardust mission (Mennella 2010).

Acknowledgements

This work has been supported by ASI research contracts.

References

- Gadallah, K. A. K., Mutschke, H., & Jager, C. 2011, *A&A* 528, A56
Gadallah, K. A. K., Mutschke, H., & Jager, C. 2012, *A&A* 544, A107
Godard, M., *et al.* 2011, *A&A* 529, 146
Mennella, V. 2008, *ApJ* 682, L101
Mennella, V. 2010, *ApJ* 718, 867
Mennella, V., Colangeli, L., Bussoletti, E., Palumbo, P., & Rotundi, A. 1998, *ApJ* 507, L177
Mennella, V., Muñoz Caro, G., Ruiterkamp, R., Schutte, W. A., Greenberg, J. M., Brucato, J. R., & Colangeli, L. 2001, *A&A* 367, 355
Mennella, V., Brucato, J. R., Colangeli, L., & Palumbo, P. 2002, *ApJ* 569, 531
Mennella, V., Baratta, G. A., Esposito, A., Ferini, G., & Pendleton, Y. J. 2003, *ApJ* 587, 727
Muñoz Caro, G., Ruiterkamp, R., Schutte, W. A., Greenberg, J. M., & Mennella, V. 2001, *A&A* 367, 347