

be playing a role in the proposed stick-slip mechanism.

TIM PALUCKA

Two-Photon Polymerization of Organically Modified Ceramics Used in 3D Microfabrication

Two-photon polymerization (2PP) of photosensitive acrylates and epoxies has been used in recent years to fabricate three-dimensional (3D) microstructures such as photonic crystals and mechanical devices. Femtosecond laser pulses, which initiate the 2PP, can achieve submicrometer resolution when tightly focused into the volume of liquid resin. B.N. Chichkov of Laser Zentrum Hannover, R. Houbertz of the Fraunhofer-Institut für Silicatforschung in Würzburg, and co-workers have extended this technique to a commercial multifunctional inorganic-organic hybrid polymer that has properties advantageous for photonic applications. They have applied this technique to the fabrication of microstructures and photonic crystals with a structure size down to 200 nm and a periodicity of 450 nm.

As reported in the March 1 issue of *Optics Letters*, the material employed for 2PP was ORMOCER, an acronym for organically modified ceramic, developed at the Fraunhofer-Institut für Silicatforschung. The researchers recognized that ORMOCERs, which are produced by a sol-gel method, have many properties important for photonics, such as an adjustable index of refraction in the range of 1.47–1.56, high optical transparency with low losses for both the resin and polymerized material, high chemical resistance, and exceptional thermal and mechanical properties. Specifically, ORMOCER-1 is designed for UV photolithography and contains the UV-sensitive Irgacure 369 initiator. All ORMOCERs are transparent in the IR and especially at 780 nm, so that Ti-sapphire laser pulses can be focused into the volume of liquid resin.

The research team used a Ti-sapphire oscillator with a repetition rate of 80 MHz, a pulse duration of 80 fs, and a laser wavelength of 780 nm. A mechanical shutter with a minimum switching time of 5 ns controlled the number of laser pulses and the radiation time. Femtosecond laser pulses were focused with a 100× oil-immersion-lens microscope objective with a numerical aperture of 1.4 and $n_{oil} = 1.515$ for index matching. The researchers said that resolution beyond the diffraction limit can be achieved because of the threshold behavior of the 2PP process.

The researchers developed expressions for the diameter and length of the polymerized volume (volume pixel, or voxel)

as functions of laser power and irradiation time. By curve-fitting the experimental data to these expressions, the researchers were able to determine the expressions' unknown parameters, which in turn define the lateral and axial resolution of the objective (340 nm and 1.2 μm , respectively).

The researchers demonstrated 3D microstructuring with femtosecond lasers and fabrication by 2PP by presenting scanning electron micrographs of a micrometer-scale statue of the Venus de Milo. The researchers scanned the laser beam with an x - y galvo scanner and moved the sample in the z direction with a translation stage. In order to speed fabrica-

tion, only the shell of the statue was irradiated with femtosecond laser pulses. After washing out the remaining liquid resin, the statue was irradiated with UV light for final polymerization of the inner body. Total fabrication time was about 5 min. The researchers also fabricated microcapsules from ORMOCER-1, which is biocompatible and can be used in medical applications. A third demonstration was the fabrication of a photonic crystal, which was built up from individual rods with diameters of 200 nm and an inter-rod spacing of 250 nm. Total fabrication time was about 10 min.

The researchers said they expect that

Cost-Effective Portable Spin Coater



Two-Stage Spinning

Dispense liquid during Stage 1
Spin-up and flatten during Stage 2


Adjustable Speed

Stage 1

500 to 2500 rpm
2 to 18 seconds

Stage 2

1,000 to 8,000 rpm
3 to 60 seconds



Vacuum Chucks

Wide Range of Vacuum Chucks
Available To Hold Different
Substrates in KW-4A Spin
Coater

KW-4A SERIES PRODUCT LINE



UV Curer
KW-4AC

Hot Plate
KW-4AH

Spin Coater
KW-4A

Dispenser
KW-4AD



CHEMAT TECHNOLOGY, INC.
9036 Winnetka Avenue, Northridge, CA 91324
1-800-475-3628, Fax: 818-727-9477
website: www.enlabproducts.com ; www.chemat.com
email: marketing@chemat.com

For more information, see <http://advertisers.mrs.org>

2PP of ORMOCERs will be used for the low-cost fabrication of artificial microstructured and nanostructured components for different applications in optics, medicine, and biology.

STEVEN TROHALAKI

Microfluidic Plugs Produce Long-Period Gratings in Microstructured Optical Fiber

With the development of wavelength-division multiplexing, bandwidth has been significantly increased over the past few years, but for continued advancement, dynamic filters and attenuators need to be developed. Researchers at OFS Labora-

tories in New Jersey have developed a microstructured optical fiber (MOF) whose wavelength-dependent attenuation can be modified by a long-period grating, composed of an alternating air/liquid refractive index, in the cladding.

As described in the March 3 issue of *Applied Physics Letters*, C. Kerbage and B. Eggleton, who is now director of the photonics research center called CUDOS at the University of Sydney in Australia, have developed a method of alternately drawing fluid (in this study, trifluorotoluene) and air into the holes of the MOF. This is achieved by repeatedly dipping a cleaved fiber in a liquid reservoir

while subjected to a vacuum on the other end of the fiber. When the fiber is submerged, it draws in liquid, and when it is not submerged, it draws in air. In order to produce attenuation in the 1550-nm communications window, a duty cycle of 125 Hz was used, corresponding to a grating period of 460 μm . While the microfluidic plugs are in the cladding of the fiber and should not strongly interact with the light propagating down the 8- μm -diameter germanium-doped core, the fiber has been tapered to extend the single-mode field into the cladding. The higher-order modes in the cladding then interact with the periodic refractive-index mismatch, causing high losses at a determined wavelength. As the fiber tapers back to its original diameter and into the single-mode fiber, the higher order modes are attenuated while the fundamental mode continues to propagate.

While the use of long-period gratings is not a new technology in fiber optics, such gratings have lacked the degree of tunability of the MOF with microfluidic plugs. With both ends of the fiber coupled to a single-mode fiber, the ends of the MOF fiber can be heated, creating an expansion of the air in the ends of the fiber. The air between the microfluidic plugs is compressed, changing the period of the grating. The fiber then exhibits wavelength tunability. According to the researchers, this type of fiber holds promise for devices in optical communication and fiber sensing.

JEFFREY R. DiMAIO

Research on Self-Assembled Monolayer Field-Effect Transistors Concludes Previous Reports are Implausible

Last year, much of J.H. Schön's innovative work at Lucent on field-effect transistors made from self-assembled dithiol monolayers was judged to be fraudulent by an independent review committee. However, questions remained within the molecular electronics community as to which, if any, of the results of Schön's discredited research could be achieved. Recently, a group of researchers from IBM T.J. Watson Research Center have investigated Schön's system to elucidate the limitations and the key requirements necessary to fabricate molecular devices. While the researchers were unable to reproduce Schön's results, they identified some of the design rules necessary to fabricate molecular devices, which include the high purity of molecules for self-assembly and a thorough characterization of the surfaces at each step of the fabrication on both molecular and device-area levels. The researchers also determined that the molecular-device structure must be characterized both structurally and electrically. In addition, the research team explained that tunneling places a lower limit on channel length, and therefore molecular length, to ~ 3 nm. In addition, electrostatics requires gate dielectrics with thicknesses of less than 2/3 the molecular length, although they are also subject to tunneling limitations.

As reported in the February issue of *Nano Letters*, C.R. Kagan and co-workers created prototypes of the devices having the structure of field-effect transistors ("trench" and planar Si structures) with self-assembled monolayers of 1,1'-biphenyl-4,4'-dithiol instead of an inorganic semiconductor. The prototypes were studied in detail after each step of preparation. The geometry of the devices on Si wafers was fabricated using lithography, reactive-ion etching, and anisotropic wet-etching techniques. After this, a uniform film of gate dielectric was formed. Source and drain electrodes were prepared by collimated evaporation of Au and Ti on the gate dielectric. Self-assembled monolayers of dithiols formed on the source electrodes were characterized by local imaging probes such as scanning tunneling and atomic force microscopies, as well as large-area characterization by, for example, contact-angle measurements and ellipsometry.

The researchers found that biphenylmonothiol and biphenyldithiol form disordered layers with, at best, small (~ 10 Å) ordered regions, and that molecules such as alkanethiols assemble to form ordered domains separated by disordered boundaries. The devices made of the well-washed monolayers of 1,1'-biphenyl-4,4'-dithiol formed electrical shorts, contrary to the characteristics reported by Schön, but consistent with the expected physics for these disordered, short molecule assemblies.

In efforts to uncover the origin of the I - V characteristics reported by Schön, the IBM research team formed molecular multilayers with longer channel lengths. The researchers, however, did not observe significant gate field effect; furthermore, they found that obtaining significant field effect and turning the device off are fundamentally impossible. Despite the evidence of recent misconduct, though, the research team said that "there is no scientific reason to lose faith in the tremendous promise of this field."

An exploration of Schön's work was also carried out by a research team in The Netherlands; see the MRS Web site at www.mrs.org/gateway/matl_news.html.

MAXIM NIKIFOROV

X-Rays Generated Using Graphite Nanofiber Cold Cathode with Copper Anode

X-ray imaging has numerous technological and medical uses. To produce x-rays, typically a heated cathode emits electrons by thermionic emission (TE); the electrons then accelerate through a high potential difference before they bombard a metal target anode. The hot-cathode method has several drawbacks, such as the short lifetime of the hot cathode as it reacts with residual gases and the low efficiency of the TE process. In the March 10 issue of *Applied Physics Letters*, researchers report the creation of a point x-ray source using a graphite nanofiber (GNF) cold cathode and a conical copper anode, yielding a high-resolution x-ray radiography system and thus eliminating the need for a cooling system required for hot-cathode sources.

The GNFs were grown on a hot steel plate by thermal chemical vapor deposition from CO and hydrogen. From their analysis of the diffraction pattern observed