

REFINEMENT OF A ONE-LAYER TRICLINIC CHLORITE

Key Words—Cation ordering, Chlorite, Crystal structure, X-ray diffraction.

Chlorite minerals commonly exhibit stacking disorder. Among those with ordered arrangements, the one-layer triclinic I**b**-4 structure is most abundant. The I**b**-4 structure was first determined by film methods (Steinfink, 1958) and subsequently refined from X-ray diffraction data by Phillips *et al.* (1980) and Zheng and Bailey (1989) and from neutron diffraction by Joswig *et al.* (1980).

The X-ray diffraction structure of the triclinic I**b**-4 chlorite presented here is the base for a comparison of the structural details of this polytype with a coexisting monoclinic I**b**-2 chlorite (Joswig *et al.*, 1989).

EXPERIMENTAL

A single crystal of I**b**-4 polytype was chosen from a sample from the Achmatow mine, Ural Mountains, U.S.S.R., which contained disordered and semi-ordered chlorites, several one-layer triclinic, two one-layer monoclinic, one two-layer triclinic, and one two-layer monoclinic polytypes of very poor quality. Microprobe analyses at eight positions in a single grain: average (in wt. %) SiO₂, 29.31; Al₂O₃, 18.50; MgO, 31.32; MnO, 0.13; K₂O, 0.04; Na₂O, 0.11; and TiO₂, Cr₂O₃, PO₄, and CaO, <0.05; and by wet-chemical analysis: FeO, 3.34 and Fe₂O₃, 2.52. The calculated

chemical formula on the basis of 28 positive charges is: (Mg_{4.54}Al_{0.97}Fe²⁺_{0.28}Fe³⁺_{0.18}Mn_{0.01})(Si_{2.85}Al_{1.15})O₁₀(OH)₈ and indicates that these chlorites are clinochlore (Bayliss, 1975).

The crystal of the triclinic I**b**-4 polytype had dimensions of 0.4 × 0.18 × 0.05 mm and was of good quality (i.e., no streaks parallel to *c**). A NONIUS CAD4 diffractometer was used for data collection. Unit-cell constants were refined from 25 reflections as follows: *a* = 5.325(2), *b* = 9.234(5), *c* = 14.358(6) Å, α = 90.33(4), β = 97.38(3), γ = 90.00(4)°. Altogether, 2459 reflections—*to* sinθ/λ = 0.7027—were collected with MoKα radiation monochromatized by pyrolytic graphite. After an empirical psi-scan absorption correction, the data set was averaged to 1966 reflections. For the refinement, 1900 reflections (*F*₀ > 5σ) were used, and a weighting scheme ω(*F*₀) = [5σ + 0.0001 · *F*₀² + 0.5]⁻¹ was employed. All atomic coordinates, anisotropic temperature factors of the nonhydrogen atoms, and an isotropic extinction parameter were refined with 143 variables. A final reliability factor *R* = 0.047 and a weighted *R*_w = 0.057 was achieved in space group *C*1̄.

The parameters are given in Table 1 and the bond lengths in Table 2.

Table 1. Atomic coordinates and thermal parameters (*U*_{*ij*} × 10⁻²) of clinochlore, Achmatow mine, U.S.S.R.

Atom	x	y	z	U ₁₁	U ₂₂	U ₃₃	U ₁₂	U ₁₃	U ₂₃
M _a (1)	0.00	0.00	0.00	0.48(5)	0.47(5)	0.96(5)	0.05(4)	0.09(4)	0.04(4)
M _a (2)	0.00127(16)	0.33382(9)	0.00003(6)	0.44(4)	0.52(4)	0.98(4)	-0.02(3)	0.12(3)	0.06(3)
T(1)	0.23211(15)	0.16809(8)	0.19257(6)	0.59(4)	0.51(4)	0.93(4)	-0.02(3)	0.13(3)	0.05(3)
T(2)	0.73204(15)	0.00138(8)	0.19252(5)	0.59(4)	0.55(4)	0.88(4)	0.01(3)	0.14(3)	0.01(3)
O(1)	0.1925(4)	0.1679(2)	0.0770(1)	0.78(9)	0.82(9)	1.14(9)	-0.08(7)	0.20(7)	0.02(7)
O(2)	0.6927(4)	0.0008(2)	0.0769(1)	0.82(10)	0.82(9)	1.13(9)	0.02(7)	0.12(7)	0.05(7)
O(3)	0.2081(5)	0.3348(3)	0.2337(2)	1.92(12)	1.29(10)	1.54(10)	-0.04(9)	0.30(8)	0.01(8)
O(4)	0.5146(4)	0.1033(3)	0.2341(2)	1.01(10)	1.80(11)	1.59(10)	0.38(9)	0.19(9)	-0.07(8)
O(5)	0.0153(4)	0.0664(3)	0.2338(2)	1.24(11)	1.93(11)	1.62(10)	-0.37(9)	0.10(8)	0.12(8)
O(6)	0.6919(4)	0.3338(2)	0.0733(2)	1.06(10)	1.02(10)	1.12(9)	0.12(8)	0.25(7)	0.11(7)
H(1)	0.717(1)	0.340(6)	0.135(4)	2.00					
M _b (1)	-0.00044(17)	0.16666(9)	0.49994(6)	0.66(4)	0.69(4)	1.44(4)	-0.04(3)	0.18(3)	0.06(3)
M _b (2)	0.00	0.50	0.50	0.33(5)	0.38(5)	1.01(5)	-0.09(4)	0.12(4)	0.05(4)
O(7)	0.1528(5)	-0.0007(3)	0.4301(2)	1.69(11)	1.66(11)	1.20(10)	-0.30(9)	0.12(8)	0.12(8)
O(8)	0.1374(5)	0.3370(3)	0.4302(2)	1.95(12)	1.84(11)	0.96(10)	-0.14(9)	0.15(8)	0.01(8)
O(9)	0.6382(4)	0.1617(3)	0.4306(2)	1.20(10)	1.82(11)	1.12(10)	0.64(9)	0.08(8)	-0.13(8)
H(2)	0.128(1)	-0.001(7)	0.369(4)	2.00					
H(3)	0.125(1)	0.335(6)	0.375(5)	2.00					
H(4)	0.613(1)	0.151(7)	0.369(5)	2.00					

Table 2. Interatomic distances (Å) of clinochlore, Achmatow mine, U.S.S.R.

<i>Tetrahedra</i>			
T(1)–O(1)	1.646(2)	T(2)–O(2)	1.647(2)
–O(3)	1.657(2)	–O(4)	1.659(3)
–O(4)	1.659(2)	–O(5)	1.659(2)
–O(5)	<u>1.657(3)</u>	–O(3)	<u>1.662(3)</u>
Mean:	1.655	Mean:	1.657
<i>Octahedra</i>			
M _t (1)–O(1)	2.089(2) × 2	M _t (2)–O(1)	2.082(2)
–O(2)	2.088(2) × 2		2.085(2)
–O(6)	<u>2.061(2) × 2</u>	–O(2)	2.080(2)
Mean:	2.079		2.084(2)
		–O(6)	2.066(3)
			<u>2.066(2)</u>
		Mean:	2.077
M _b (1)–O(7)	2.062(3)	M _b (2)–O(8)	1.994(3) × 2
	2.060(3)	–O(7)	1.987(2) × 2
–O(8)	2.055(3)	–O(9)	<u>1.992(2) × 2</u>
	2.061(3)	Mean:	1.991
–O(9)	2.050(2)		
	<u>2.052(3)</u>		
Mean:	2.057		

RESULTS AND DISCUSSION

Joswig *et al.* (1989) reported the neutron diffraction refinement of a coexisting monoclinic *I**b**-2* polytype. Both the *I**b**-2* and the *I**b**-4* polytypes showed a similar ordering pattern in the 2:1 layer and the interlayer sheets; the octahedral cations in the 2:1 layer were disordered ($M_t(1)–O = 2.079$ Å; $M_t(2)–O = 2.077$ Å), whereas Al^{VI} predominantly occupies the $M_b(2)$ site ($M_b(1)–O = 2.057$ Å; $M_b(2)–O = 1.991$ Å) compared with $M_b(1)–O = 2.055$ Å and $M_b(2)–O = 1.997$ Å of the coexisting monoclinic polytype, where the subscript t and b represent the 2:1 layer and brucite-like sheet, respectively. Thus, as a consequence no significant difference within experimental error was found between the coexisting monoclinic *I**b**-2* and the triclinic *I**b**-4* polytypes, in contrast with the finding of Zheng and Bailey (1989) for intergrown monoclinic and triclinic polytypes. The two independent T sites were found to be disordered: $T(1)–O = 1.655$, $T(2)–O = 1.657$ Å. This result is identical to the neutron diffraction refinement of a triclinic *I**b**-4* penninite (Joswig *et al.*, 1980).

The refined hydrogen positions in the triclinic polytype were nearly the same as determined by neutron diffraction of a penninite sample (Joswig *et al.*, 1980). Therefore, the same hydrogen bonding pattern must be present. The high estimated standard deviations, however, prevent a detailed discussion. As noted by Phillips *et al.* (1980), the ordering of a trivalent cation in the M(4) (= $M_b(2)$) site increased the angle α of the lattice constants. Table 3 gives the dependence of the angle α from the degree of ordering in the two independent octahedral positions of the interlayer sheet.

*Institut für Kristallographie
und Mineralogie
Universität Frankfurt/Main
6000 Frankfurt
Federal Republic of Germany*

WERNER JOSWIG
HARTMUT FUESS

REFERENCES

- Bayliss, P. (1975) Nomenclature of the trioctahedral chlorites: *Canadian Mineral.* **13**, 178–180.
Joswig, W., Fuess, H., and Mason, S. A. (1989) Neutron

Table 3. Angle α in triclinic *I**b*** chlorite samples as an indicator of cation ordering in the interlayer sheet.

	α (°)	$M_b(1)$ (Å)	$M_b(2)$ (Å)	Δ (Å)
Penninite (Joswig <i>et al.</i> , 1980)	89.95(1)	2.045	2.023	0.022
Clinochlore (this work)	90.33(4)	2.057	1.991	0.066
Chromian clinochlores (Phillips <i>et al.</i> , 1980)	90.45(3)	2.069	1.963	0.106
	90.53(6)	2.075	1.960	0.115
Clinochlore (Zheng and Bailey, 1989)	90.48(2)	2.078	1.956	0.122

- diffraction study of a one-layer monoclinic chlorite: *Clays & Clay Minerals* (in press).
- Joswig, W., Fuess, H., Rothbauer, R., Takéuchi, Y., and Mason, S. A. (1980) A neutron diffraction study of a one-layer triclinic chlorite (penninite): *Amer. Mineral.* **65**, 349–352.
- Phillips, T. L., Loveless, J. K., and Bailey, S. W. (1980) Cr³⁺ coordination in chlorites: A structural study of ten chromian chlorites: *Amer. Mineral.* **65**, 112–122.
- Steinfink, H. (1958) The crystal structure of chlorite. II. A triclinic polymorph: *Acta Crystallogr.* **11**, 195–198.
- Zheng, H. and Bailey, S. W. (1989) The structures of intergrown triclinic and monoclinic IIb chlorites from Kenya. *Clays & Clay Minerals* **37**, 308–316.

(Received 23 September 1988; accepted 25 July 1989; Ms. 1834)